

**THOMSON**  
DELPHION

RESEARCH

PRODUCTS

INSIDE DELPHION

[Home](#) | [About Delphion](#) | [Contact Us](#) | [My Account](#) | [Products](#)
[Search: Quick/Number](#) | [Boolean](#) | [Advanced](#) | [Derwent](#)

## The Delphion Integrated View

 Get Now: ☒ PDF | [More choices...](#)

 Tools: Add to Work File: [Create new Work File](#)

 View: [INPADOC](#) | Jump to: [Top](#) | Go to: [Derwent](#)
[Email this to a](#)

**Title: JP59063668A2: THERMAL ACTIVATING BATTERY**

**Derwent Title:** Heat-activated battery - comprising electrolyte and positive and negative active materials where separator is removed by heat to activate  
NoAbstract NoDwg [\[Derwent Record\]](#)

**Country:** JP Japan  
**Kind:** A

**Inventor:** SAOTOME ISAO;  
ARAKAWA TATSUMI;  
FUKUOKA MASAYUKI;

**Assignee:** ASAHI CHEM IND CO LTD  
[News, Profiles, Stocks and More about this company](#)

**Published / Filed:** 1984-04-11 / 1982-10-05

**Application Number:** JP1982000173936

**IPC Code:** [H01M 6/36](#); [H01M 10/39](#);

**Priority Number:** 1982-10-05 JP1982000173936


**Abstract:** PURPOSE: To provide a battery which outputs no power during storage and outputs power by heating by separating at least either one of a cathode active material, electrolyte, and an anode active material in a battery with a spacer such as paraffine.

CONSTITUTION: Nickel is used as a current collector 1, and paraffine having a melting point of 60 ~ 62°C is used as a spacer 4 which separates a negative active material 5 from electrolyte 3. Zinc plate is used as the negative active material 5. A positive mix 2 consists of acetylene black, manganese dioxide, and ammonium chloride. Electrolyte consists of ammonium chloride and zinc chloride mixed solution. Thickness of paraffine is 0.5mm or less. This battery outputs no current and voltage at room temperature. When the battery is placed in the air at 80°C for 30sec, it produces current and voltage and after 2 seconds, the battery outputs a power of 1.5V, 100mA/cm<sup>2</sup>.

COPYRIGHT: (C)1984,JPO&Japio

**Family:** None

**Other Abstract Info:** None



## Best Available Copy



[Nominate](#)

[this for the Gallery...](#)

© 1997-2004 Thomson      [Research Subscriptions](#) | [Privacy Policy](#) | [Terms & Conditions](#) | [Site Map](#) | [Contact Us](#) | [Help](#)



(19)

(11) Publication number: **590636**

Generated Document.

**PATENT ABSTRACTS OF JAPAN**(21) Application number: **57173936**(51) Intl. Cl.: **H01M 6/36 H01M 10/39**(22) Application date: **05.10.82**

(30) Priority:	(71) Applicant: <b>ASAHI CHEM IND CO LTD</b>
(43) Date of application publication: <b>11.04.84</b>	(72) Inventor: <b>SAOTOME ISAO ARAKAWA TATSUMI FUKUOKA MASAYUKI</b>
(84) Designated contracting states:	(74) Representative:

**(54) THERMAL  
ACTIVATING BATTERY**


(57) Abstract:

**PURPOSE:** To provide a battery which outputs no power during storage and outputs power by heating by separating at least either one of a cathode active material, electrolyte, and an anode active material in a battery with a spacer such as paraffine.

**CONSTITUTION:** Nickel is used as a current collector 1, and paraffine having a melting point of 60~62°C is used as a spacer 4 which separates a negative active material 5 from electrolyte 3. Zinc plate is used as the negative active material 5. A positive mix 2 consists of acetylene black, manganese dioxide, and ammonium chloride. Electrolyte consists of ammonium chloride and zinc chloride mixed solution. Thickness of paraffine is 0.5mm or less. This battery outputs no current and voltage at room temperature. When the

battery is placed in the air at 80°C for 30sec, it produces current and voltage and after 2 seconds, the battery outputs a power of 1.5V, 100mA/cm<sup>2</sup>.

COPYRIGHT: (C)1984,JPO&Japio



Best Available Copy